

## TECHNICAL DATA SHEET

## M110

## Polypropylene Homopolymer

### Characteristics

**M110** is a **Polypropylene Homopolymer**, produced by the latest generation **Spheripol II Technology**. This homopolymer is primarily suitable for **Injection Molding Process**.

**M110** combines **exceptional processability with low Cycle Time, high Gloss & excellent Color & Processing Stability**.

### Application

- General Purpose Injection Molding
- Furniture

Property	Test Method	Unit	Value
Melt Flow Index (2.16 kg & 230 <sup>0</sup> C)	ASTM D 1238	g/10 min	11
Density at 23°C	ASTM D 1505	g/cm <sup>3</sup>	0.90
Tensile Strength at Yield (50 mm/min)	ASTM D 638	MPa	34
Tensile Elongation at Yield (50 mm/min)	(Type I - with Extensometer)	%	9
Flexural Modulus	ASTM D 790A	MPa	1450
Notched Izod Impact Strength (23°C)	ASTM D 256A	J/m	30
Vicat Softening Point (10N)	ASTM D 1525	<sup>0</sup> C	154
Heat Deflection Temperature (0.455 MPa)	ASTM D 648	<sup>0</sup> C	99

### Typical Processing Temperature

Barrel Temperature	<sup>0</sup> C	180 - 280
Mold Temperature	<sup>0</sup> C	30 – 40

*Mechanical properties are tested on Injection Molded Test Specimens prepared as per ASTM D 4101*

*The information & data presented herein are typical values and should not be construed as specification. No warranty or guarantee expressed or implied is made regarding performance. The information & data are subject to change without prior intimation based on research & development work undertaken by the company.*

Compliance Certificates & MSDS are available on request.

Visit us at [www.haldiapetrochemicals.com](http://www.haldiapetrochemicals.com)